



## Polymeric Material Spreading Rates

| Mils  | US Gallon       |                | Imperial Gallon |                | Liter           |                |
|-------|-----------------|----------------|-----------------|----------------|-----------------|----------------|
|       | ft <sup>2</sup> | m <sup>2</sup> | ft <sup>2</sup> | m <sup>2</sup> | ft <sup>2</sup> | m <sup>2</sup> |
| 1.00  | 1,604.0         | 149.0          | 1,926.0         | 178.9          | 423.8           | 39.4           |
| 1.50  | 1,069.0         | 99.3           | 1,284.0         | 119.3          | 282.4           | 26.2           |
| 2.00  | 802.0           | 74.5           | 963.2           | 89.5           | 211.9           | 19.7           |
| 2.50  | 614.6           | 59.6           | 770.6           | 71.6           | 169.5           | 15.7           |
| 3.00  | 534.7           | 49.7           | 642.2           | 59.7           | 141.3           | 13.1           |
| 3.50  | 458.3           | 42.6           | 550.4           | 51.2           | 121.1           | 11.3           |
| 4.00  | 401.4           | 37.3           | 481.6           | 44.8           | 105.9           | 9.9            |
| 4.50  | 356.4           | 33.1           | 428.0           | 39.8           | 94.2            | 8.7            |
| 5.00  | 320.8           | 29.8           | 385.3           | 35.9           | 84.8            | 7.9            |
| 6.00  | 267.3           | 24.8           | 321.0           | 29.8           | 70.6            | 6.6            |
| 7.00  | 229.1           | 21.3           | 275.1           | 25.6           | 60.5            | 5.6            |
| 8.00  | 200.5           | 18.6           | 240.8           | 22.3           | 53.0            | 4.9            |
| 9.00  | 178.2           | 16.6           | 214.0           | 19.9           | 47.1            | 4.4            |
| 10.00 | 160.4           | 14.9           | 192.6           | 17.9           | 42.4            | 3.9            |