



## Polymeric Material Spreading Rates

Mils	US Gallon		Imperial Gallon		Liter	
	ft <sup>2</sup>	m <sup>2</sup>	ft <sup>2</sup>	m <sup>2</sup>	ft <sup>2</sup>	m <sup>2</sup>
1.00	1,604.0	149.0	1,926.0	178.9	423.8	39.4
1.50	1,069.0	99.3	1,284.0	119.3	282.4	26.2
2.00	802.0	74.5	963.2	89.5	211.9	19.7
2.50	614.6	59.6	770.6	17.6	169.5	15.7
3.00	534.7	49.7	642.2	59.7	141.3	13.1
3.50	458.3	42.6	550.4	51.2	121.1	11.3
4.00	401.4	37.3	481.6	44.8	105.9	9.9
4.50	356.4	33.1	428.0	39.8	94.2	8.7
5.00	320.8	29.8	385.3	35.9	84.8	7.9
6.00	267.3	24.8	321.0	29.8	70.6	6.6
7.00	229.1	21.3	275.1	25.6	60.5	5.6
8.00	200.5	18.6	240.8	22.3	53.0	4.9
9.00	178.2	16.6	214.0	19.9	47.1	4.4
10.00	160.4	14.9	192.6	17.9	42.4	3.9