



TM Grout Resin

Modified Epoxy Resin with added Synthetic Filler

DESCRIPTION

TM Grout Resin is a high solids, modified epoxy resin with added synthetic filler. This product provides a sealed barrier layer between **underlayment systems**. As well as providing the initial seal coat in the Terrazzo M Base Coat system. TM Grout Resins main purpose is to fill all porous voids in the prior system that it is applied to, leaving the installer with a jointless surface to apply the next layer of a desired system.

Theoretical Coverage Rates

0.01inches	0.254 mm	10 mils
110 Square Feet Per Kit		

0.015	0.381 mm	15 mils
73 Square Feet Per Full Kit		

Kit and Packaging sizes (1 Kit = Resin + Hardener)

Item Number	Description	Component	Weight
1414	TM Grout Resin	Part. E	5.0lbs / 2.26
1415	TM Grout Resin Hardener	Part. F	2.5lbs / 1.13

Installation Guideline for TM Grout Resin

Step1: Pre-mix both components of the TM Grout Kit, due to its higher than normal viscosity this step is crucial. When both components are mixed, they can then be combined and mixed together for 2 min.

Step2: Pour the contents of the TM Grout Sealer onto the working surface (**Underlayment system** or **Terrazzo M Base-Coat**) using a Squeegee trowel spread the mixture generously making sure to fill any porous spots in the underlayment or base coat.

Step3: Allow to sit for 30-45 seconds per spread; this allows the TM Grout Resin to seep into the underlayment or base coat more effectively. Back roll with an epoxy nap roller to ensure full coverage.
Back rolling with an epoxy nap roller is optional

Step4: Using the squeegee trowel ; squeegee off all excess material and repeat the process over again until all material is used.

***** POT LIFE FOR TM GROUT RESIN TENDS TO BE LESS THAN NORMAL EPOXY. EXPECT 20-30 min OF POT LIFE PER CAN. POT LIFE CAN BE EXTENDED BY POURING THE CONTENTS OF THE CAN DIRECTLY ONTO THE WORKING SURFACE AFTER MIXED TOGETHER. THIS MAY EXTEND POT LIFE FOR 5-10min*****

TM Grout Resin

Modified Epoxy Resin with added Synthetic Filler

Surface Preparation

Light sanding can be done to underlayment before the TM Grout Resin is applied but is not necessary for the system to be effective. If applying to Terrazzo M Base coat, scrape the cured basecoat with a trowel to remove any dried material from the surface. Then proceed to apply TM Grout Resin. For a more in-depth description of TM Grout Resin applied to Terrazzo M Base Coat please refer to the corresponding **Application Spec.**

Job Site Survey

Measure and record ambient temperature and humidity, surface temperature and the temperature of the material being used. Do not proceed with the application if the conditions are outside the recommended parameters. Inspect materials to be used. Verify material is the proper material and all components and sizes are correct. Inspect all containers and verify a proper factory seal with no signs of damage or leakage. Premix Liquid materials into a smooth homogenous blend before uses.

Environmental Conditions for Application

All materials are mixed, applied and cured at the job site. Minimum environmental conditions are required to facilitate proper curing and performance of the products. Ensure conditions are in accordance with the following requirements.

Substrate Temp	Min. 45°F	Max. 95°F
Max Relative humidity	Min. <90%	Max. 90%
Ambient Air Temp	Min. 45°F	Max.100°F

Dry to Re-Coat	14Hrs at 65°F	10Hrs at 75°F	08Hrs at 85°F
Max Re-Coat	48Hrs at 65°F	44Hrs at 75°F	40Hrs at 85°F
Cure to Full Service	52Hrs at 65°F	48Hrs at 75°F	44Hrs at 85°F

Material Disclosure

Materials should be delivered in original packages and containers with seals unbroken and bearing manufacturer's labels containing brand name and directions for storage and mixing with other components. Check materials immediately upon receipt, verify all the correct materials in the correct packaging are accounted for in good condition. Sort the materials and store them in a tempered storage area.

Applicator Notes

For proper workability it is important the Dex-O-Tex materials be stored and mixed at a temperature of 65°F-80°F. A warm substrate will decrease the pot life and make the materials sticky. A cooler substrate will lengthen the cure time and may cause a blush of the polymeric resins. Decking surfaces and room temperature of 65°F or slightly higher must be maintained for the duration of the Cure to Full Service time. When mixing the polymeric resin components, be sure to use all the provided resins. The resins are premeasured to the correct ratios. Scrape all the hardener from the container into the resin. Do not turn mixing vessels upside down to drain on the flooring surface. Unmixed resin from the side may produce soft or uncured spots on the flooring surface. Keep the unfinished flooring surface clean. Do not track dirt, grease, or any other contaminates onto the unfinished decking surface. Any contaminate could negatively affect the aesthetics of the finished flooring. Good ventilation must be provided during application, particularly in confined spaces. Always obtain, read and observe Manufacturers Safety Data Sheets (**MSDS**) before handling polymeric materials.

Warranty Information

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP.'S INVOICE ARE MET. CROSSFIELD PRODUCTS CORP. WARRANTS TO THE PURCHASER OF ITS PRODUCTS THAT SUCH PRODUCTS ARE FREE FROM MANUFACTURING DEFECT. CROSSFIELD DOES NOT WARRANT OR GUARANTEE THE WORKMANSHIP PERFORMED BY ANY PERSON OR FIRM INSTALLING ITS PRODUCTS. CROSSFIELD'S OBLIGATION UNDER THIS WARRANTY IS LIMITED SOLELY TO THE ORIGINAL PURCHASER AND SOLELY TO THE REMEDY OF REPLACEMENT IN KIND OF ANY PRODUCT WHICH CROSSFIELD SOLD WHICH MAY PROVE DEFECTIVE IN MANUFACTURE WITHIN ONE YEAR FROM DATE OF INSTALLATION, PROVIDED SAID PRODUCT WAS STORED CORRECTLY AND INSTALLED WITHIN THE PRODUCT'S SHELF LIFE, BY THE ORIGINAL PURCHASER AND WHICH CROSSFIELD EXAMINATION SHALL DISCLOSE TO CROSSFIELD'S SATISFACTION TO BE THUS DEFECTIVE. IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES

Notes:

