



## Colorflake/TM Sealer

Modified and Refined Epoxy Sealer Resin

### DESCRIPTION

**Colorflake/TM Sealer** is a 100% solids, modified epoxy sealer resin. This product provides a uniform high gloss finish to existing decorative surfaces such as Colorflake M Epoxy, Terrazzo M Basecoat, Terrazzo M Quik-Step, and Elastaflake. Fluid-applied to form a jointless surface; Colorflake/TM Sealer offers substantial protection against everyday wear and tear in high traffic areas. This clear finish can also be incorporated with a non-skid aggregate to create a high strength slip-resistant protective surface.

### Theoretical Coverage Rates

#### Minimum Application Thickness = Maximum Product Coverage

<b>0.003 inches</b>	<b>0.0762mm</b>	<b>7 mils</b>
170 Square Feet Per 1 Kit		

#### Maximum Application Thickness = Minimum Product Coverage

<b>0.005 inches</b>	<b>0.127mm</b>	<b>12 mils</b>
100 Square Feet Per 1 Kit		

#### Kit and Packaging Sizes (1 Kit = Resin + Hardener)

Item Number	Description	Components	Gross Weight
1265	Colorflake/TM Sealer Resin (0.5 GL; 1 GL Can)	Part A	6.5 lb / 2.95 kg
1266	Colorflake/TM Sealer Hardener (0.25 GL; 1 QT Can)	Part B	3.0 lb / 1.36 kg
0527	Colorflake/TM Sealer Resin-Hardener Kit (0.75 GL)	Part A & B	9.5 lb / 4.32 kg

### Installation Guideline for Colorflake/TM Sealer

**Step1:** Pour mixed contents of **Colorflake/TM Sealer** onto a properly prepared and cured Epoxy or Terrazzo and spread using a notched squeegee or epoxy roller. Colorflake/TM Sealer can also be applied by pouring mixed contents into a paint tray and using an epoxy roller; roll from the paint tray onto the working surface.

**Step2:** If needed, back roll with a short nap epoxy roller to smooth out any imperfections. \*If out-gassing occurs, back roll again after 3 -5 minutes.

\*This may be an indication of undergrouting.

**Step3:** If a **non-skid finish** is required, blend non-skid aggregate into mixed sealer, pour contents into a painting tray and then apply from the painting tray with an epoxy nap roller.

## Surface Preparation

New deck covering should be sealed within the critical cure time. If this time has elapsed or for existing deck surfaces, clean to be free of all contaminants. Grease and oil should be removed with approved solvents and clean rags in accordance with SSPC SP-1. The resulting surface should be clean and have some surface profile before Dex-O-Tex materials are applied. This can be achieved by lightly sanding the existing floor with 220 grit or similar sand paper. Consult your local Dex-O-Tex Marine Rep when wood or other deck surfaces are involved.

## Job Site Survey

Measure and record ambient temperature and humidity, surface temperature and the temperature of the material being used. Do not proceed with the application if the conditions are outside the recommended parameters. Inspect materials to be used. Verify material is the proper material and all components and sizes are correct. Inspect all containers and verify a proper factory seal with no signs of damage or leakage. Premix liquid materials into a smooth homogenous blend before uses.

## Environmental Conditions for Application

All materials are mixed, applied and cured at the job site. Minimum environmental conditions are required to facilitate proper curing and performance of the products. Ensure conditions are in accordance with the following requirements.

<b>Substrate Temp</b>	Min 45°F	Max 95°F
<b>Max Relative Humidity</b>	Min <20%	Max 90%
<b>Ambient Air Temp</b>	Min 45°F	Max 100°F

<b>Dry to Re-Coat or Use</b>	10 Hrs at 65°F	8 Hrs at 75°F	06 Hrs at 85°F
<b>Max Re-Coat</b>	48 Hrs at 65°F	44 Hrs at 75°F	40 Hrs at 85°F
<b>Cure to Full Service</b>	52 Hrs at 65°F	48 Hrs at 75°F	44 Hrs at 85°F

## Material Disclosure

Materials should be delivered in original packages and containers with seals unbroken and bearing manufacturer's labels containing brand name and directions for storage and mixing with other components. Check materials immediately upon receipt, verify all the correct materials in the correct packaging are accounted for in good condition. Sort the materials and store them in a tempered storage area.

## Applicator Notes

For proper workability it is important the Dex-O-Tex materials be stored and mixed at a temperature of 65°F-80°F. A warm substrate will decrease the pot life and make the materials sticky. A cooler substrate will lengthen the cure time and may cause a blush of the polymeric resins. Decking surfaces and room temperature of 65°F or slightly higher must be maintained for the duration of the Cure to Full Service time. When mixing the polymeric resin components, be sure to use all the provided resins. The resins are premeasured to the correct ratios. Scrape all the hardener from the container into the resin. Do not turn mixing vessels upside down to drain on the flooring surface. Unmixed resin from the side may produce soft or uncured spots on the flooring surface. Keep the unfinished flooring surface clean. Do not track dirt, grease, or any other contaminants onto the unfinished decking surface. Any contaminate could negatively affect the aesthetics of the finished flooring. Good ventilation must be provided during application, particularly in confined spaces. Always obtain, read and observe Manufacturers Safety Data Sheets (SDS) before handling polymeric materials.

## Warranty Information

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP.'S INVOICE ARE MET. CROSSFIELD PRODUCTS CORP. WARRANTS TO THE PURCHASER OF ITS PRODUCTS THAT SUCH PRODUCTS ARE FREE FROM MANUFACTURING DEFECT. CROSSFIELD DOES NOT WARRANT OR GUARANTEE THE WORKMANSHIP PERFORMED BY ANY PERSON OR FIRM INSTALLING ITS PRODUCTS. CROSSFIELD'S OBLIGATION UNDER THIS WARRANTY IS LIMITED SOLELY TO THE ORIGINAL PURCHASER AND SOLELY TO THE REMEDY OF REPLACEMENT IN KIND OF ANY PRODUCT WHICH CROSSFIELD SOLD WHICH MAY PROVE DEFECTIVE IN MANUFACTURE WITHIN ONE YEAR FROM DATE OF INSTALLATION, PROVIDED SAID PRODUCT WAS STORED CORRECTLY AND INSTALLED WITHIN THE PRODUCT'S SHELF LIFE, BY THE ORIGINAL PURCHASER AND WHICH CROSSFIELD EXAMINATION SHALL DISCLOSE TO CROSSFIELD'S SATISFACTION TO BE THUS DEFECTIVE. IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES

## Notes: