



Decor-Flor IMO Sealer

Modified IMO Epoxy Sealer Resin
 Referenced in USCG- USCG-164.106/65/0

DESCRIPTION

Decor-Flor IMO Sealer is a high solid, modified IMO approved epoxy sealer resin. This product provides a uniformed clear finish to existing decorative surfaces such as Terrazzo, Urethanes and Epoxies. Fluid-applied to form a jointless surface; Decor-Flor IMO Sealer offers substantial protection against everyday wear and tear in high traffic areas. This clear finish can also be incorporated with a non-skid aggregate to create a high strength non-slipping protective surface.

Theoretical Coverage Rates

Recommended *minimum* application thickness

0.005 inches	0.12 mm	5 mils
215 Square Feet Per 1 Kit		

Recommended *average* application thickness

0.007 inches	0.17 mm	7 mils
153 Square Feet Per 1 Kit		

Recommended *maximum* application thickness

0.008 inches	0.20 mm	8 mils
134 Square Feet Per 1 Kit		

Kit and Packaging sizes (1 Kit = Resin + Hardener)

Item Number	Description	Components	Weight
0460-IMO	Décor-Flor IMO Sealer Resin	Part. A	4.5lbs / 2.05 KG
0461-IMO	Décor-Flor IMO Sealer Resin Hardener	Part. B	2.75lbs / 1.24KG

Installation Guideline for Decor-Flor IMO Sealer over Decor-Flor Base

Step1: Pour mixed contents of Decor-Flor IMO Sealer onto cured Decor-Flor Base and Quartz and spread using a notched squeegee or epoxy roller. Decor-Flor IMO Sealer can also be applied by pouring mixed contents into a paint tray and using an epoxy roller; roll from the paint tray onto the working surface.

Step2: If needed back roll with an epoxy loop roller to smooth out any imperfections. ***If out-gassing occurs back roll with an epoxy spiked roller***

Step3: If a **non-skid finish** is required. Blend non-skid aggregate into mixed sealer, pour contents into a painting tray and then apply from the painting tray with an epoxy nap roller.

**** Décor-Flor IMO Sealer can also be applied over a cured ColorflakeM IMO system****

****This ensures a complete IMO compliant system ****

Decor-Flor IMO Sealer

Modified IMO Epoxy Sealer Resin
 Referenced in USCG- USCG-164.106/65/0

Surface Preparation

Existing deck surfaces should be cleaned free of rust, loose scale, and dirt. Grease and oil should be removed with approved solvents and clean rags in accordance with SSPC SP-1. The resulting surface should be clean and have some surface profile before Dex-O-Tex materials are applied. This can be achieved by lightly sanding the existing floor with 220 grit or similar sand paper. Consult your local Dex-O-Tex Marine Rep. when wood or other deck surfaces are involved.

Job Site Survey

Measure and record ambient temperature and humidity, surface temperature and the temperature of the material being used. Do not proceed with the application if the conditions are outside the recommended parameters. Inspect materials to be used. Verify material is the proper material and all components and sizes are correct. Inspect all containers and verify a proper factory seal with no signs of damage or leakage. Premix Liquid materials into a smooth homogenous blend before uses.

Environmental Conditions for Application

All materials are mixed, applied and cured at the job site. Multiple environmental conditions are required to facilitate proper curing and performance of the products. Ensure conditions are in accordance with the following requirements.

Substrate Temp	Min. 50°F	Max. 80°F
Max Relative humidity	Min. <90%	Max. 85%
Ambient Air Temp	Min. 50°F	Max.95°F

Dry to Re-Coat or Use	12Hrs at 65°F	10Hrs at 75°F	08Hrs at 85°F
Max Re-Coat	48Hrs at 65°F	44Hrs at 75°F	40Hrs at 85°F
Cure to Full Service	56Hrs at 65°F	48Hrs at 75°F	44Hrs at 85°F

Material Disclosure

Materials should be delivered in original packages and containers with seals unbroken and bearing manufacturer's labels containing brand name and directions for storage and mixing with other components. Check materials immediately upon receipt, verify all the correct materials in the correct packaging are accounted for in good condition. Sort the materials and store them in a climate-controlled storage area.

Applicator Notes

For proper workability it is important the Dex-O-Tex materials be stored and mixed at a temperature between 65°F-80°F. A warm substrate will decrease the pot life and make the materials sticky. A cooler substrate will lengthen the cure time and may cause a blush of the polymeric resins. Decking surfaces and room temperature of 65°F or slightly higher must be maintained for the duration of the Cure to Full Service time. When mixing the polymeric resin components, be sure to use all the provided resins. The resins are premeasured to the correct ratios. Scrape all the hardener from the container into the resin. Do not turn mixing vessels upside down to drain on the flooring surface. Unmixed resin from the side may produce soft or uncured spots on the flooring surface. Keep the unfinished flooring surface clean. Do not track dirt, grease, or any other contaminates onto the unfinished decking surface. Any contaminate could negatively affect the aesthetics of the finished flooring. Good ventilation must be provided during application, particularly in confined spaces. Always obtain, read and observe manufacturers Safety Data Sheets (**SDS**) before handling polymeric materials.

Decor-Flor IMO Sealer

Modified IMO Epoxy Sealer Resin
Referenced in USCG- USCG-164.106/65/0

Warranty Information

NO WARRANTY SHALL BE EFFECTIVE UNTIL THE TERMS AND CONDITIONS OF SALE SET FORTH IN CROSSFIELD PRODUCTS CORP.'S INVOICE ARE MET. CROSSFIELD PRODUCTS CORP. WARRANTS TO THE PURCHASER OF ITS PRODUCTS THAT SUCH PRODUCTS ARE FREE FROM MANUFACTURING DEFECT. CROSSFIELD DOES NOT WARRANT OR GUARANTEE THE WORKMANSHIP PERFORMED BY ANY PERSON OR FIRM INSTALLING ITS PRODUCTS. CROSSFIELD'S OBLIGATION UNDER THIS WARRANTY IS LIMITED SOLELY TO THE ORIGINAL PURCHASER AND SOLELY TO THE REMEDY OF REPLACEMENT IN KIND OF ANY PRODUCT WHICH CROSSFIELD SOLD WHICH MAY PROVE DEFECTIVE IN MANUFACTURE WITHIN ONE YEAR FROM DATE OF INSTALLATION, PROVIDED SAID PRODUCT WAS STORED CORRECTLY AND INSTALLED WITHIN THE PRODUCT'S SHELF LIFE, BY THE ORIGINAL PURCHASER AND WHICH CROSSFIELD EXAMINATION SHALL DISCLOSE TO CROSSFIELD'S SATISFACTION TO BE THUS DEFECTIVE. IN NO EVENT SHALL CROSSFIELD PRODUCTS CORP. BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. THIS WARRANTY IS EXPRESSLY GIVEN IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR USE AND ALL OTHER OBLIGATIONS OR LIABILITIES ON CROSSFIELD'S PART, AND WE NEITHER ASSUME NOR AUTHORIZE ANY PERSON OR PERSONS TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF A CROSSFIELD PRODUCT. THIS WARRANTY SHALL NOT APPLY TO ANY OF CROSSFIELD'S PRODUCTS, WHICH HAVE BEEN SUBJECT TO ADULTERATION, ALTERATION, ABUSE OR MISUSE. CROSSFIELD PRODUCTS CORP. MAKES NO WARRANTY WHATSOEVER IN RESPECT TO ACCESSORIES, PARTS OR MATERIALS NOT SUPPLIED BY CROSSFIELD PRODUCTS CORP., WHICH ARE USED IN CONNECTION WITH ITS PRODUCTS. THE TERM "ORIGINAL PURCHASER" IN THIS WARRANTY MEANS THAT PERSON, CORPORATION OR ENTITY TO WHOM CROSSFIELD PRODUCTS CORP. SOLD ITS PRODUCT OR PRODUCTS. ANY ACTION TO ENFORCE ANY WARRANTY OR FOR BREACH OF CONTRACT OR ARISING OUT OF ANY CLAIM AGAINST CROSSFIELD PRODUCTS CORP. SHALL BE COMMENCED AND MAINTAINED ONLY IN A COURT OF COMPETENT JURISDICTION IN THE CONTINENTAL UNITED STATES OF AMERICA. THE PURCHASER ACCEPTS THESE TERMS AND CONDITIONS, AND HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES

Notes: